



a subsidiary of Garland Industries, Inc.

Paint Reflectivity Information

Effective June 2015

SRI = Solar Reflectance Index

SR = Solar Reflectivity

E = Emissivity Rating

Color #	Color / Texture	SR	SRI	E	
1101	Charcoal	0.32	32	0.85	STANDARD
185	Almond Suede	0.42	46	0.86	
1102	Moss Green	0.35	36	0.85	
135	Blue Sapphire	0.16	12	0.86	
187	Chestnut	0.30	30	0.86	
125	Epic Bronze	0.07	1	0.88	
112	Solar White	0.67	80	0.84	
184	Cadet Gray	0.39	42	0.85	
1103	Steel Gray	0.22	20	0.86	
141	Sandstone	0.54	63	0.86	
183	Colonial Red	0.31	31	0.85	
129	Opal Star	0.72	88	0.85	
146	Emerald Forest	0.12	6	0.85	
121	Silver Cloud	0.46	52	0.86	
1104	Conch Shell	0.53	62	0.90	
181	Weathered Copper	0.30	31	0.87	
189	Wedgewood	0.32	32	0.85	
191	Cardinal Red	0.40	42	0.82	
1105	August Moon	0.60	70	0.85	
1106	Matte Black	N/A	N/A	N/A	
1107	Night Horizon	0.07	-1	0.84	
161	Georgian Brick	0.35	37	0.87	PREMIUM
1108	Gray Velvet	0.19	14	0.83	
1109	Metallic Brick	0.30	30	0.85	
120	Brite Copper	0.49	55	0.85	
157	Platinum Silver	0.60	68	0.77	
159	Prewathered Galvalume	0.33	31	0.80	
1110	Light Bronze	0.55	64	0.86	DA VINCI
1010	Soft Graphite	N/A	N/A	N/A	
1015	Cerulean Shadow	N/A	N/A	N/A	
1017	Carmine Blush	N/A	N/A	N/A	
1018	Verdian Mist	N/A	N/A	N/A	
1019	Umber Glaze	N/A	N/A	N/A	
1020	Carbon Cast	N/A	N/A	N/A	

For Valspar paint codes or information regarding discontinued colors, please contact IMETCO.

Due to variances among color monitors, printers, and environment lighting, the colors that appear above may not be exact and are for reference only. Please contact your IMETCO representative to request a free metal color sample before selecting your final color.